


S2048C Technical Data

Extra Long Machine Tape



Product Composition



Colours



Description	OPP Film with Acrylic Adhesive
Features/Benefits	Economical High adhesion Good temperature resistance
Areas of Use	Carton sealing High volume carton sealing
Applicable Industries	Packaging Transport/shipping
Standard Sizes Available	48mm x 2000m = 3 rolls / carton
Slitting Options	Not Applicable

Backing (Liner)	OPP Film
Adhesive Type	Acrylic
Tensile Strength N/25mm	98
Elongation at Break %	150
Temperature Resistance °C	70
Adhesion to Stainless Steel N/25mm	9
Total Thickness (mm)	0.045 (45 Microns)

The figures above are based off average results from multiple tests, results may vary + or - 5%

Pomona & Selfgard™ products are registered and under trademark of Pomona Group Ltd and sold exclusively through selected distributors.

For further information on Pomona or Selfgard™ please email sales@pomona.co.nz, phone **0800 POMONA (0800 766662)** or contact your distributor.

Conditions of Use

For best results apply self adhesive tapes between 15°C and 25°C in a dry environment. Application surfaces must be dry and free from dust and particles. Do not apply on surfaces treated or contaminated by anti-adhesives. Avoid contact with surfaces containing plasticizers or other chemical agents not compatible with the tape. In cases of rough or irregular surfaces, it is better to use a tape with a higher quantity of adhesive. Care must be taken with reference to removability without residue and working conditions of the self adhesive tape.

Tape Storage

Ideally store tape between 15°C and 25°C with a maximum relative humidity of 65%. Always store away from heat sources, avoiding exposure to light and if possible keep in the original packaging. When temperatures are lower than 15°C it is highly recommended to recondition the adhesive tape to normal temperatures (15°C to 25°C) before use.

Tape Shelf Life

Self-adhesive tapes technical features are generally not permanent but remain at their best for approximately 12 months, if stored according to suggested conditions and by avoiding extreme environmental conditions such as quick and sudden temperature changes, exposure to UV light and high levels of humidity.

All test methods are based on ASTM standards and Pomona's standardised test methods. The information provided above is based on our experience and tape industry knowledge. It is given in good will but is not intended as a guarantee or a warranty. All end users should ensure for themselves that the product is suitable for their own particular application before using. NB: Peak Force Test: based on ASTM 3759/D ASTM 3759/M and Pomona® test methods, Peel Test: based on ASTM D3330 and Pomona® test methods.

Pomona & Selfgard™ products are registered and under trademark of Pomona Group Ltd and sold exclusively through selected distributors.

For further information on **Pomona** or **Selfgard™** please email sales@pomona.co.nz, phone **0800 POMONA (0800 766662)** or contact your distributor.

Pomona Group Limited
POSTAL: PO Box 21806 | Henderson | Auckland 0650

AUCKLAND: 3 Hickory Avenue | Henderson | Auckland 0612
CHRISTCHURCH: 16 Brisbane Street | Sydenham | Christchurch 8023



100% NZ Owned and Operated

www.pomona.co.nz