

TECHNICAL DATA SHEET

Automatic Length Tape Dispenser

Product Code **S8989**



pomona
we do it better

Pomona Group Limited
PO Box 21806, Henderson
Auckland 0650
P 0800 766 662
www.pomona.co.nz

SPECIFICATIONS

CODE	S8989
DESCRIPTION	Automatic Length Tape Dispenser
FEATURES AND BENEFITS	Electronic control for precision length adjustment Fast, continuous operation, or manual control Dispenses double sided, printed message, cloth, masking and electrical tapes Saves time and tape wastage
AREAS OF USE	Ideal for production lines and packaging areas

PHYSICAL PROPERTIES

DIMENSIONS (MM)	137W x 218D x 150H
WEIGHT (KG)	2.4
APPLICABLE TAPE WIDTH (MM)	7 - 50
TAPE LENGTH SETTING RANGE (MM)	Auto range: 5 - 999 free setting

The figures above are based off average results from multiple tests, results may vary + or - 5%

Tapes / Gloves / Work Protection
100% New Zealand Owned & Operated

S8989 DECEMBER 2022

CONDITIONS OF USE

For best results apply self-adhesive tapes between 15°C and 25°C in a dry environment. Application surfaces must be dry and free from dust and particles. Do not apply on surfaces treated or contaminated by anti-adhesives. Avoid contact with surfaces containing plasticizers or other chemical agents not compatible with the tape. Care must be taken regarding removability without residue and working conditions of the self-adhesive tape.

TAPE STORAGE

Ideally, store tape between 4°C and 26°C with a maximum relative humidity between 40% and 50%. Always store away from heat sources, avoiding exposure to light and if possible keep in the original packaging. Rotation of stock is recommended. When temperatures are lower than 15°C, it is highly recommended to recondition the adhesive tape to the average temperature range (4°C to 26°C) before use.

TAPE SHELF LIFE

Self-adhesive tapes technical features are generally not permanent but remain at their best for approximately 12 months, if stored according to suggested conditions and by avoiding extreme environmental conditions such as quick and sudden temperature changes, exposure to UV light and high levels of humidity.

OTHER INFORMATION

All test methods are based on ASTM standards and Pomona's standardised test methods. The information provided above is based on our experience and tape industry knowledge. It is given in goodwill but is not a guarantee or a warranty. All end-users should ensure for themselves that the product is suitable for their particular application before using.

NB: Peak Force Test: based on ASTM 3759/D ASTM 3759/M and Pomona® test methods,
Peel Test: based on ASTM D3330 and Pomona® test methods.

Pomona & Selfgard™ products are registered and under trademark of Pomona Group Ltd & sold exclusively through selected distributors.

For further information on **Pomona** or **Selfgard™** please email sales@pomona.co.nz, phone **0800 0800 766662** or contact your distributor.

Tapes / Gloves / Work Protection
100% New Zealand Owned & Operated